


# LAMFLOCK



## LAMINAS DE FLOCK PARA TRANSFERENCIA TERMICA HOT STAMPING FLOCK PAPERS

APLICACIÓN: ADHESIVO TF aplicado en malla 34-29 sobre tejido blanco, presecado 100°C 1min. y transferido en plancha 180°C 12 segundos.  
APPLICATION: ADHESIVE TF printed with mesh 34-29 filaments/cm2 on white fabric, dried 100°C 1min. Transfer with iron 180°C 12 seconds.

PRODUCTOS RECOMENDADOS / RECOMMENDED PRODUCTS:  
ADHESIVO TF (BASE AGUA, WATER BASED) / TEXPLAST TRANSFER (PLASTISOL)

